



## 产品规格书/Specification

产品/product:	导电银浆/ Silver paste
料号/Part number:	01H-6602B

### 适用范围/Application:

一种高粘度，低流动性的银浆，适合于印刷间隔较小的电路，同时适合电磁导热行业使用。

### 使用条件/Operating conditions:

基材 Substrate	陶瓷/玻璃 Ceramic, glass
印刷 Printing	200-300 目丝网印刷 200-300 mesh stainless screen
流平 Levelling	5-15min minutes at room temperature 室温下流平 5-15 分钟（时间根据流平的实际情况决定）。
干燥 Drying	通风烘箱烘烤 100-150℃，10-15 分钟 （空考温度低于 300℃，可根据烘烤的实际情况决定烘烤时间。） 100-150℃ 10-15 min
烧结 Firing Condition	隧道炉空气气氛下烧结，峰值 700℃（推荐值），9-11 分钟。 （可根据实际需要，烧结范围可在 550-750℃内调节,但峰值温度时间必须 10 分钟。） Atmospheric firing in belt furnace with peak time of 9-11 Minutes at 700℃
Thinner	ST-1000

### 性能/Characteristics:

#### 1. 浆料性能/Paste Characteristics:

性能 Characteristic	标准 Standard	测试方法及条件 Test method and conditions
1 Fineness	≤5μm	FOG test
2 Viscosity	250-450Pa.s	Brookfield HBT utility cup and spindle (SC4-14/6R), 10rpm, 25±1℃,  Brookfield HBT (博利飞) 粘度计, 转子 SC4-14/6R), 10rpm, 25±1℃ 粘度可根据用户实际需要调节。

#### 2. 烧结后特性/Characteristics after firing:

在 1 烧结条件下，膜厚 8-12μm Check fired film produced under the conditions specified in 1), (Film thickness is 8-12μm.)



深圳市賽雅電子漿料有限公司  
Shenzhen Sryeo Electronic Paste Co., Ltd.

Tel: 0755-28078692 Fax: 0755-28078687

[www.sryeo.com](http://www.sryeo.com)(中文) [www.sryeo.net](http://www.sryeo.net) (Eng.) [sales@sryeo.com](mailto:sales@sryeo.com)

特性 Characteristics	Standard 标准	测试方法和条件 Test method and conditions
3 Resistivity 方阻	$\leq 5\text{m}\Omega/\square$	Test pattern 0.6mm×60mm 测试图形 0.6mm×60mm
4 Adhesion strength 附着力		Peel Test: 0.5mm $\phi$ Tin plated Cu wire soldered on 2mm×2mm Pad. 0.5mm $\phi$ 锡浸铜线, 焊接面积 2mm×2mm Solder: 96.5Sn/0.5Cu Mildly activated flux used. 焊料: 96.5Sn/0.5Cu
Initial 初始附着力	$\geq 45.2\text{N}$	
Ageing 老化附着力	$\geq 24.6\text{N}$	Ageing: 150°C×24hrs 老化条件: 150°C, 24 小时

**保存条件, 有效期/Storage condition and Term of validity**

产品应在 5-25°C 的环境温度下密封储存, 有效期为产品发货之日起 1 年。

The product shall be guaranteed for 1 year after shipping date, keep tightly under at 5-25°C

**包装方式/Packaging method:**

标准包装, 1000g/罐, Standard package: 1000g/can

样品装, 200 克/罐 Sample package: 200g/can