



产品规格书/Specification

产品/product:	介质浆料浆料/ Dielectric paste
料号/part number:	07M-CR04

适用范围/Application:

该款浆料适合于贴片电阻，贴片保险丝一次包封。

The paste is suitable to chip resistor, chip fuse first package for adjust resist .

使用条件/Operating conditions:

基材 Substrate	氧化铝陶瓷 Alumina ceramic
使用方法 Method of use	印刷，200-250 目 Printing, 200-250mesh
流平 Levelling	5-10min minutes at room temperature 室温下流平 5-10 分钟（时间根据流平的实际情况决定）。
烘干 Curing conditions	通风烘箱烘烤 100-150℃，10-15 分钟 （空考温度低于 300℃，可根据烘烤的实际情况决定烘烤时间。） 100-150℃ 10-15 min
烧结 Firing Condition	隧道炉空气气氛下烧结，峰值 600℃（推荐值），10 分钟。 Atmospheric firing in belt furnace with peak time of 10 Minutes at 720℃
稀释剂 Thinner	ST-1001

性能/Characteristics:

1. 浆料性能/Paste Characteristics:

性能 Characteristic	标准 Standard	测试方法及条件 Test method and conditions
1 细度 Fineness	≤8μm	FOG test
2 粘度 Viscosity	100~200Pa.s	Brookfield HBT utility cup and spindle (SC4-14/6R), 10rpm, 25±1℃, 博利飞粘度计， 转子 SC4-14/6R), 10rpm, 25±1℃
3 Appearance 外观	浅绿色 Light green	



2. 烧结后特性/Characteristics after curing:

在 1 烧结条件下,

Characteristics	Standard	Test method and conditions
4 外观 Appearance	紧凑, 致密 Compact and Dense	目视 Eyeballing
5 Acid-resistant 抗酸性	Good 良好	Eyeballing, 5% H ₂ SO ₄ for 30min 目测 5% H ₂ SO ₄ 30 分钟

保存条件, 有效期/Storage condition and Term of validity

产品应在 5-15°C 的环境温度下密封储存, 有效期为产品发货之日起 1 年。

The product shall be guaranteed for 1 year after shipping date, keep tightly under at 5-15°C

包装方式/Packaging method:

标准包装, 1000g/罐, 样品可提供 200 克小罐包装

Standard package 1000g/can, if you need sample to test, available 200g with small package.